


Imaging

Images do not accurately portray size or color.

Accu-Vu™ Imaging:



Comments:

General Report Comments:

Document No: 1148501 A and B Validation Date: 27 May 2025

Identification

Mineral Type: Natural Corundum Transparency: Transparent

Variety: Ruby Color Description: Red

Carat Weight: 0.93 and 0.88 cts Shape: Round

Measurements: 5.96 - 5.88 x 3.26 mm Cutting Style: Mixed Cut
and 5.95 - 5.90 x 3.15 mm

Comments: Two gemstones with a total weight of 1.81 cts.

Identification

American Gemological Laboratories™
America's first and most highly respected origin lab.

Founded in 1977,
AGL is an internationally recognized gemstone
testing facility, specializing in comprehensive
colored stone analyses.

AGL has the distinction of being the
first laboratory in the United States to issue
Country-of-Origin reports. Our company and its
principals have a long tradition of research into the
detection of and reporting on gem identification-
and-classification, gemstone treatments and
provenance determinations.

Our staff is composed of experts in the field
of gemstone testing and reporting. Our findings
reflect the latest knowledge and analytical
techniques to ensure the highest standards
are applied on every stone we test.

AGL's testing and reporting
methodology provide you with unsurpassed quality
and reliability. We are committed to providing
the highest level of service and reporting
that our clients and the industry have
come to expect from the AGL.

Origin

Provenance: Burma (Myanmar)

Comments: Based on available gemological information, it is the opinion of the Laboratory that the origin of this material would be classified as Burma (Myanmar - Mong Hsu).



Origin

Enhancement

Standard: Heat Additional: Clarity

Stability Index: Color Stability: Excellent Degree: Insignificant to Minor

Type: Heating Residues

Stability Index: Excellent to Very Good

Comments: Rubies are commonly heated to modify their color and appearance. Heating residues are deposited along healed fissures during the heating process.

Enhancement

1	2	3	4	5	6	7	8	9	10
Excellent	Very Good	Good	Fair	Poor					

Enhancement Stability Index™

None	Insignificant	Minor	Moderate	Strong	Prominent
Extremely Rare	Very Rare	Rare	Uncommon	Common	Very Common

Degree of Clarity Enhancement & Relative Rarity™

M. Chaipaksa
Monrudee Chaipaksa, Senior Gemologist

Christopher P. Smith
Christopher P. Smith, President

